



Steel Strapping Chart

Regular Duty Steel Strapping

Width	Thickness	Avg. Strength	Yield	Coil Winding	
Inch	Inch	Pounds	Ft./lb	Oscillated	Ribbon
3/8	.015	675	52.4	X	
	.020	880	39.3	X	
1/2	.015	870	39.3	X	
	.020	1,170	29.4	X	
	.023	1,300	25.6	X	
5/8	.015	1,125	31.4	X	
	.020	1,460	23.6	X	
	.023	1,670	20.5	X	
3/4	.015	1,350	26.2	X	
	.020	1,750	19.6	X	
	.023	1,950	17.1	X	
	.028	2,300	14	X	



Oscillated Wound

Regular duty strapping is a low carbon, cold rolled steel strapping.

High Tensile Steel Strapping

Width	Thickness	Avg. Strength	Yield	Coil Winding	
Inch	Inch	Pounds	Ft./lb	Oscillated	Ribbon
1/2	.020	1,450	29.4	X	
	.023	1,660	25.6	X	
5/8	.020	1,810	23.6	X	
	.023	2,050	20.5	X	
3/4	.020	2,150	19.6	X	
	.023	2,450	17.1	X	
	.025	2,620	15.7	X	X
	.029	3,050	13.1	X	X
	.031	3,250	12.7	X	X
1 1/4	.020	3,825	11.8		X
	.025	4,650	9.4		X
	.029	5,250	8.1		X



Ribbon Wound

High Tensile strapping is a specially blended cold rolled steel product that is heat treated and quickly cooled to maximum elongation for high shock specifications.

	.031	5,400	7.6		X
	.035	6,150	6.7		X
	.044	7,610	5.3		X
2	.044	12,300	3.3		X